

The aggregate shall meet the requirements of WSDOT Std. Spec #9-03.4 "Crushed Screening for bituminous surface treatment" with the following exceptions:

Percent Passing by weight	<u>Sieve Size</u>	<u>1/2" - #4</u>	<u>3/8" - #4</u>	<u>3/8" - #10</u>	<u>1/4" - #10</u>
	5/8" square	100	-----	-----	-----
	1/2" square	95 - 100	100	100	-----
	3/8" square	60-85	70-90	95-100	100
	1/4" square	-----	-----	-----	95-100
	# 4	0-5	0-5	0 - 20	0-60
	#10	-----	-----	0-5	0-10
	#200	0-1	0-1	0-1	0-1